Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-09-26 **Date: 31/05/2021**

me : "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

s Reference : BBMP/EE/BTP/WO/142/2019-20

ceipt : 26-05-21

ID : Cement Concrete Pavement . (RO Plant Road (church Back Side road))

pe /Size : 150X150X150 mm

ade/Age : M30 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

t : 31/05/2021

dentification Mark	**Grade of concrete**	**Date of Casting**	**Date of Testing**	**Dimension of the Specimen** (mm)	**Cross sectional area** (Sq.mm)	**Weight of the sample** (kg)	**Failure Load** (KN)	**Compressive strength** (N/mm^2)	**Average Compressive Strength** (N/mm^2)
ment Concrete Pavement	M30	24/05/2021	31/05/2021	150.97 X 151.49 X 149.11	22869	**8.576**	592.1	25.9	25.7
ment Concrete Pavement	M30	24/05/2021	31/05/2021	149.37 X 151.21 X 149.99	22587	**8.888**	608.0	26.9	
ment Concrete Pavement	M30	24/05/2021	31/05/2021	151.72 X 149.71 X 151.02	22714	**8.211**	549.0	24.2	

obtained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.

CIVIL Pro Sig.. BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-09-26 **Date: 21/06/2021**

ame : "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd. #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

's Reference : BBMP/EE/BTP/WO/142/2019-20

eceipt : 26-05-21

r ID : Cement Concrete Pavement , (RO Plant Road (church Back Side road))

ype /Size : 150X150X150 mm

rade/Age : M30 / 28 Days Compressive Strength

e to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

est : 21/06/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
ement Concrete Pavement	M30	24/05/2021	21/06/2021	149.50 X 149.56 X 150.21	22359	**9.070**	744.2	33.3	32.9
ement Concrete Pavement	M30	24/05/2021	21/06/2021	150.54 X 151.25 X 149.39	22770	**9.031**	731.5	32.1	
ement Concrete Pavement	M30	24/05/2021	21/06/2021	149.92 X 149.43 X 149.07	22403	**9.057**	742.5	33.1	

lts obtained are satisfactory as per standard requirements.

AEE (WR)/SD

CIVIL Pro Sig..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-09-26** **Date: 01/06/2021**

ame : "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd. #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

r's Reference : BBMP/EE/BTP/WO/142/2019-20

eceipt : 27-05-21

r ID : Cement Concrete Pavement (10th Cross Road)

ype /Size : 150X150X150 mm

rade/Age : M30 / 7 Days Compressive Strength

e to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

est : 01/06/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement	M30	25/05/2021	01/06/2021	149.73 X 149.18 X 149.67	22337	**8.576**	580.4	26.0	25.6
Cement Concrete Pavement	M30	25/05/2021	01/06/2021	150.57 X 149.76 X 149.37	22548	**8.888**	587.7	26.1	
Cement Concrete Pavement	M30	25/05/2021	01/06/2021	150.25 X 151.02 X 151.68	22691	**8.211**	563.8	24.8	

lts obtained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.

CIVIL Pro Sig..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-09-26** **Date: 22/06/2021**

e : "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

Reference : BBMP/EE/BTP/WO/142/2019-20

ipt : 27-05-21

) : Cement Concrete Pavement (10th Cross Road)

e /Size : 150X150X150 mm

le/Age : M30 / 28 Days Compressive Strength

BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 22/06/2021

ntification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
ent Concrete avement	M30	25/05/2021	22/06/2021	151.91 X 150.35 X 149.57	22839	**9.070**	763.6	33.4	33.0
ent Concrete avement	M30	25/05/2021	22/06/2021	151.59 X 149.93 X 151.90	22727	**9.031**	739.6	32.5	
ent Concrete avement	M30	25/05/2021	22/06/2021	151.30 X 149.90 X 149.12	22680	**9.057**	750.7	33.1	

btained are satisfactory as per standard requirements.

AEE (VRP) SD

CIVIL Pro Sig..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

: CP-2020-12-09-26

Date: 01/06/2021

: "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

Name : Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

: BBMP/EE/BTP/WO/142/2019-20

's Reference : 27-05-21

Receipt : Cement Concrete Pavement (10th Cross Road)

ID : 150X150X150 mm

Type /Size : M30 / 7 Days Compressive Strength

grade Age : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

nce to BIS codes : 01/06/2021

of test

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement	M30	25/05/2021	01/06/2021	150.94 X 151.48 X 151.31	22864	**8.576**	584.9	25.6	25.5
Cement Concrete Pavement	M30	25/05/2021	01/06/2021	151.54 X 150.51 X 151.33	22809	**8.888**	601.7	26.4	
Cement Concrete Pavement	M30	25/05/2021	01/06/2021	151.79 X 149.01 X 149.19	22618	**8.211**	558.3	24.7	

esults obtained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.

CIVIL PRO Sig..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

	: CP-2020-12-09-26	**Date: 22/06/2021**
Name of Work	: "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."	
Client Name	: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.	
Agency	: BBMP/EE/BTP/WO/142/2019-20	
Customer's Reference	: 27-05-21	
Date of Receipt	: Cement Concrete Pavement (10th Cross Road)	
Customer ID	: 150X150X150 mm	
Sample Type /Size	: M30 / 28 Days Compressive Strength	
Sample grade/Age	: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5	
Reference to BIS codes	: 22/06/2021	
Date of test		

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M30	25/05/2021	22/06/2021	150.36 X 151.39 X 151.63	22763	**9.070**	768.0	33.7	33.3
2	Cement Concrete Pavement	M30	25/05/2021	22/06/2021	151.23 X 151.48 X 149.79	22908	**9.031**	746.4	32.6	
3	Cement Concrete Pavement	M30	25/05/2021	22/06/2021	151.52 X 150.86 X 149.90	22859	**9.057**	765.6	33.5	

The results obtained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.
Sig.....
R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-09-26

Date: 03/06/2021

: "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd. #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

's Reference : BBMP/EE/BTP/WO/142/2019-20

Receipt : 29-05-21

ID : Cement Concrete Pavement (3rd Cross Road Pateel Chowdry Road)

Type /Size : 150X150X150 mm

grade/Age : M30 / 7 Days Compressive Strength

to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

test : 03/06/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement	M30	27/05/2021	03/06/2021	151.65 X 150.87 X 151.31	22880	**8.576**	573.5	25.1	25.4
Cement Concrete Pavement	M30	27/05/2021	03/06/2021	151.02 X 150.89 X 149.28	22787	**8.888**	609.6	26.8	
Cement Concrete Pavement	M30	27/05/2021	03/06/2021	149.92 X 151.64 X 151.33	22734	**8.211**	553.4	24.3	

sults obtained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.

CIVIL Pro Sig..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-09-26 **Date: 24/06/2021**

: "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

: BBMP/EE/BTP/WO/142/2019-20

: 29-05-21

: Cement Concrete Pavement (3rd Cross Road Pateel Chowdry Road)

: 150X150X150 mm

: M30 / 28 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 24/06/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
ment Concrete Pavement	M30	27/05/2021	24/06/2021	149.34 X 149.55 X 149.36	22334	**9.070**	756.3	33.9	33.3
ment Concrete Pavement	M30	27/05/2021	24/06/2021	149.68 X 149.49 X 150.83	22376	**9.031**	721.2	32.2	
ment Concrete Pavement	M30	27/05/2021	24/06/2021	150.97 X 151.31 X 150.32	22843	**9.057**	773.5	33.9	

obtained are satisfactory as per standard requirements.

AEE (VRP) SD

CIVIL Pro Sig..... BANGALORE

FOR CIVIL Pro.

R HARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

GHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-09-26 **Date: 03/06/2021**

: "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

: BBMP/EE/BTP/WO/142/2019-20

Reference : 29-05-21

ipt : Cement Concrete Pavement (3rd Cross Road Pateel Chowdry Road)

: 150X150X150 mm

Size : M30 / 7 Days Compressive Strength

Age : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

BIS codes : 03/06/2021

ntification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
ent Concrete Pavement	M30	27/05/2021	03/06/2021	149.18 X 150.69 X 151.30	22480	**8.576**	572.4	25.5	25.5
ent Concrete Pavement	M30	27/05/2021	03/06/2021	149.85 X 149.66 X 149.98	22427	**8.888**	586.6	26.2	
ent Concrete Pavement	M30	27/05/2021	03/06/2021	151.83 X 150.88 X 150.90	22908	**8.211**	567.4	24.8	

btained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.

CIVIL Pro BANGALORE Sig.....

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

GHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No : TC-5548

TEST REPORT OF CEMENT CONCRETE CUBES

Format No: CP/TF/01

: CP-2020-12-09-26

Date: 24/06/2021

ame : "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

's Reference : BBMP/EE/BTP/WO/142/2019-20

Receipt : 29-05-21

of ID : Cement Concrete Pavement (3rd Cross Road Pateel Chowdry Road)

Type /Size : 150X150X150 mm

Grade/Age : M30 / 28 Days Compressive Strength

ce to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

est : 24/06/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement	M30	27/05/2021	24/06/2021	149.74 X 151.43 X 151.82	22675	**9.070**	761.9	33.6	
Cement Concrete Pavement	M30	27/05/2021	24/06/2021	150.24 X 150.71 X 151.36	22643	**9.031**	746.3	33.0	33.3
Cement Concrete Pavement	M30	27/05/2021	24/06/2021	151.52 X 151.88 X 149.51	23013	**9.057**	765.9	33.3	

sults obtained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.

CIVIL Pro Sig. BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-09-26 **Date: 04/06/2021**

: "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd. #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

: BBMP/EE/BTP/WO/142/2019-20

: 31-05-21

: Cement Concrete Pavement (Gudde Vinayaka temple back Side)

: 150X150X150 mm

: M30 / 7 Days Compressive Strength

: IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

: 04/06/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
ement Concrete Pavement	M30	28/05/2021	04/06/2021	150.09 X 149.70 X 151.84	22468	**8.576**	570.7	25.4	25.7
ement Concrete Pavement	M30	28/05/2021	04/06/2021	149.52 X 149.23 X 150.85	22313	**8.888**	596.4	26.7	
ement Concrete Pavement	M30	28/05/2021	04/06/2021	149.84 X 150.15 X 151.72	22498	**8.211**	558.6	24.8	

lts obtained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.

CIVIL Pro Sig..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

GHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: **CP-2020-12-09-26** **Date: 25/06/2021**

ame : "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

's Reference : BBMP/EE/BTP/WO/142/2019-20

Receipt : 31-05-21

of ID : Cement Concrete Pavement (Gudde Vinayaka temple back Side)

Type /Size : 150X150X150 mm

grade/Age : M30 / 28 Days Compressive Strength

ce to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

est : 25/06/2021

Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
Cement Concrete Pavement	M30	28/05/2021	25/06/2021	151.18 X 149.40 X 151.97	22586	**9.070**	753.5	33.4	33.0
Cement Concrete Pavement	M30	28/05/2021	25/06/2021	151.32 X 151.07 X 150.40	22860	**9.031**	735.4	32.2	
Cement Concrete Pavement	M30	28/05/2021	25/06/2021	151.12 X 151.23 X 149.47	22853	**9.057**	767.3	33.6	

sults obtained are satisfactory as per standard requirements.

AEE (WRP) SD

CIVIL Pro Sig..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-09-26 **Date: 04/06/2021**

: "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd, #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

: BBMP/EE/BTP/WO/142/2019-20

, Reference : 31-05-21

ceipt : Cement Concrete Pavement (Gudde Vinayaka temple back Side)

ID : 150X150X150 mm

pe/Size : M30 / 7 Days Compressive Strength

ode/Age : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

to BIS codes : 04/06/2021

dentification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
ment Concrete Pavement	M30	28/05/2021	04/06/2021	151.80 X 151.16 X 151.42	22947	**8.576**	587.0	25.6	25.6
ment Concrete Pavement	M30	28/05/2021	04/06/2021	149.56 X 151.10 X 151.00	22599	**8.888**	608.9	26.9	
ment Concrete Pavement	M30	28/05/2021	04/06/2021	149.62 X 150.59 X 150.43	22531	**8.211**	545.7	24.2	

ts obtained are satisfactory as per standard requirements.

AEE (VRP) SD

CIVIL Pro Sig..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

: 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

IGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

CIVIL PRO
AN ISO 9001 : 2008 COMPANY & NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2017
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TE/01

TEST REPORT OF CEMENT CONCRETE CUBES

: CP-2020-12-09-26 **Date: 25/06/2021**

: "Improvements to Roads and Drains at Kuvempunagara 2nd Stage and Surrounding Area in Ward No.11 Kuvempunagara."

: Executive Engineer, Karnataka Rural Infrastructure Development Ltd. #280, 59th Cross Road, 17th 'C' Main Road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.

: BBMP/EE/BTP/WO/142/2019-20

Reference : 31-05-21

ript : Cement Concrete Pavement (Gudde Vinayaka temple back Side)

: 150X150X150 mm

e Size : M30 / 28 Days Compressive Strength

le Age : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

g BIS codes : 25/06/2021

ntification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
ment Concrete Pavement	M30	28/05/2021	25/06/2021	151.12 X 151.74 X 150.26	22931	**9.070**	767.2	33.5	33.1
ment Concrete Pavement	M30	28/05/2021	25/06/2021	150.21 X 151.63 X 150.02	22777	**9.031**	729.4	32.0	
ment Concrete Pavement	M30	28/05/2021	25/06/2021	151.09 X 151.57 X 151.55	22900	**9.057**	772.1	33.7	

ts obtained are satisfactory as per standard requirements.

AEE (VRP) SD

FOR CIVIL Pro.

CIVIL Pro BANGALORE

Sig..... R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
IGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | ENVIRONMENTAL
WATER TESTING | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES